



pinturas de la peña
fábrica de pinturas

PEÑAPLAST STANDARD IN POWDER

Indoor paste in powder (thin coat)

Page 1 to 3

Paste indicated to indoor places to cover surfaces of plaster or cement.

Features



Useful life (S/ITE C1/51-L)	7 - 8 Hours
Fire resistente	A1- Non combustible
Particle size	300 microns - Medium
pH (S/ITE CI/18-L)	6 - 7
Shore C Hardness (S/ITE CI/22-L)	81
Setting (S/ITE CI/50-L)	More than 8 hours
Tool cleaning	With water
Kg of powder used per m ² /1 mm thickness	1,20 - 1,25
Kg of paste used per m ² /1 mm thickness	1,65 - 1,80
Adhérence (S/Anexe 2 NF P 74202-1 DTU 59.2)	
To acrylic paint	Greater than 0,5 MPa
To cement	Greater than 0,5 MPa
Density (S/ITE CI/53-L) Powder	0,97 Gr/Lt
Density (S/ITE CI/53-L) Paste	1,74 Gr/Lt
Drying time in depth (S/ITE CI/52L)	
Concrete (Average thickness - 1mm coat)	4 - 5 hours
Paint (Average thickness - 1mm coat)	5 - 6 hours
Cement (Average thickness - 1mm coat)	3 - 4 hours
Packaging	15 Kg. sacks
Conservation	Keep away from extreme temperatures

Use

Knead with water at a rate of 38 to 43 percent. For each sack of 15 kg., 5,70 to 6,45 liters of water must be used for his kneading.

The knead must be manually or mechanically using an electric beater. Let the dough a few minutes, then apply. To cover with that block with cavities, a medium-sized spatula, which allows you to press firmly towards the inside of the bowl is recommended. If it is possible, to ensure that the width of the spatula is slightly greater than the size of the cavity.

The smoothing operation always vertically from top to bottom with blade, hardware and remove excess, ensuring smooth and hide all defects on surfaces. Joints are on the contrary, top to bottom. When dry, sanding and then plaster hand will be horizontally from right to left, left to right joints.

Finally, after this second hand drying, sand the surface and if there is no imperfection, go to paint on.

Properties and use

Normal setting.

Easy-to-apply, smoothing and sanding.

Applicable in thin coat.

It fill defects in the wood.

It fills the pores of the wood.

Smoothing walls with defects (scratches, scratches, blows, etc.)

MAXIMUM OF 1 MM THICK



Distribuidor Oficial de:

Note: This information is based on our current knowledge, so the piece of information is general. It describes our products and gives an orientation on how to apply and use our products. Due to the big variety, use conditions and surfaces, it cannot be taken as warranty or object of liability.

Address (Factory and offices)
Ctra. Orgaz, s/n
Apdo. 25 - 45400 Mora (Toledo)
Ph: +34 925 300 409 f: +34 925 341 082
e: info@delapenia.com



Máster
Internacional
de Empresas



Empresa Certificada en fabricación
y diseño de pinturas al agua.

www.delapenia.com



Trofeo CC100
Compromiso a
la calidad

Delegation
C/Manzanares, 1
13250 Daimiel (Ciudad Real)
Ph: +34 926 851 102
e: info.daimiel@delapenia.com



pinturas de la peña
fábrica de pinturas

PEÑAPLAST STANDARD IN POWDER

Indoor paste in powder (thin coat)

Page 2 to 3

Application

The surface must be healthy, clean, consistent, dry, free from all traces of nitrate, fungi, microorganisms, dust, grease or any type of question that might interfere with the adhesion of the product to surface.

Useful Information

The manufacturing process is batch-checked to ensure traceability. The quality control system includes the design of every item, in addition to raw material controls to ensure the uniformity and quality of the end-product. The use of eco-technology in the manufacturing processes at our facilities enables us to efficiently carry out our work without damaging the environment.

Non inflammable product.

Avoid contact with skin and eyes. Smoking, eating and drinking must be prohibited in the application zone. Comply with legislation on safety and hygiene in the workplace. Keep product in a dry place, in properly closed, original containers. Store containers between 5°C and 35°C.

First Aid - Personal protection measures

Inhalation: Although inhalation does not pose any specific risk, the use of a filter mask is recommended for prolonged use.

Eye contact: Remove contact lenses. Wash eyes with plenty of clean cold water for at least 10 minutes, pulling up the eyelids, and seek medical attention. Use protective glasses.

Contact with skin: Wash with water and soap or an appropriate skin cleanser. Protective creams may help to protect exposed skin.

Ingestion: If the product is accidentally swallowed, seek immediate medical attention. Do not induce vomiting.

Observations

For a good use and correct application of the product, the previous reading of your worksheet is essential. The data described in this manual have been obtained under normal laboratory and standard support and may vary depending on the conditions of implementation (absorption of support, applied thickness, water mixture, temperature and humidity).

The working conditions of the users, are beyond our control.

The product should not be used for purposes other than those specified.

Strictly follow the recommendations. Pre-knowledge for each application, the status of the base is essential.

It is recommended that you read carefully the section **surface preparation**.

Use the product in its lifetime.

After this time, the adverse properties can be obtained.

Established time both for its setting and the lifetime of the product are calculated in normal laboratory conditions, so are approximate and may vary depending on environmental conditions.

Do not mix with any material, as do maintain do not their technical specifications.

Do not apply on non-absorbent bases.

Supports traditional water paint finishes. If you have any question, it is recommended that you perform a test on the plaster before painting.

The permanent state of heat is not appropriate in the plaster of the range, because their mineral components contain clays or flame retardant. Therefore, it is strongly discouraged apply overheated funds. You don't want to get wet media. The products in the range have to hold the mixing water, allowing good handling without pulling.



Distribuidor Oficial de:

Note: This information is based on our current knowledge, so the piece of information is general. It describes our products and gives an orientation on how to apply and use our products. Due to the big variety, use conditions and surfaces, it cannot be taken as warranty or object of liability.

Address (Factory and offices)
Ctra. Orgaz, s/n
Apdo. 25 - 45400 Mora (Toledo)
Ph: +34 925 300 409 f: +34 925 341 082
e: info@delapenia.com



Máster
Internacional
de Empresas



Empresa Certificada en fabricación
y diseño de pinturas al agua.

www.delapenia.com



Trofeo CC100
Compromiso a
la calidad

Delegation
C/Manzanares, 1
13250 Daimiel (Ciudad Real)
Ph: +34 926 851 102
e: info.daimiel@delapenia.com



pinturas de la peña
fábrica de pinturas

PEÑAPLAST STANDARD IN POWDER

Indoor paste in powder (thin coat)

Page 3 to 3

DE LA PEÑA components are usually hygroscopic and absorb the moisture in the air. It is imperative to always apply under relative humidity conditions.

The application of the product on the old paintings that can break with the application of plaster is not recommended.

Our technical-sales team is at your disposal to help you with any queries that you may have.

According to the Royal Decree 363/1995 (Directive 67/548/EC) and the Royal Decree 255/2003 (Directive 1999/45/EC), not this classified as dangerous product. Data sheet security available to the professional user who requests it.



Distribuidor Oficial de:

Note: This information is based on our current knowledge, so the piece of information is general. It describes our products and gives an orientation on how to apply and use our products. Due to the big variety, use conditions and surfaces, it cannot be taken as warranty or object of liability.

Address (Factory and offices)
Ctra. Orgaz, s/n
Apdo. 25 - 45400 Mora (Toledo)
Ph: +34 925 300 409 f: +34 925 341 082
e: info@delapenia.com



Máster
Internacional
de Empresas



Empresa Certificada en fabricación
y diseño de pinturas al agua.

www.delapenia.com



Trofeo CC100
Compromiso a
la calidad

Delegation
C/Manzanares, 1
13250 Daimiel (Ciudad Real)
Ph: +34 926 851 102
e: info.daimiel@delapenia.com