



pinturas de la peña
fábrica de pinturas

WATER POLYURETHANE MEMBRANE

Waterborne Polyurethane Membrane for a waterproofing in transitable places Page 1 de 2

Water polyurethane membrane mono component ecological, stable to UVA rays, 100% Waterproof application liquid base highly elastic, application in situ used for the waterproofing of roofs, balconies and terraces. It prevents the penetration of water and long the life of the roof. Because of its high tenacity, it withstands medium and intense pedestrian traffic (but not vehicles). respects the environment. Not recommended for water tanks.

Features



Color	Colorless, transparent
Finishing	Glossy
Specific weight	1,04 +/-0,02 gr./cc.
Viscosity on having trippled	80 K.U. to 25 °C
Fixed material %	36% +/- 5
Solid on volume %	35% +/- 5
Performance	5 - 6 m ² /Lt. per coat depending on the state of the surface
No. Coats	Minimum 2
Minimum recommended thickness	55-59 microns per coat
Drying time at touch	3 - 4 hours (according thickness applied)
Stepable	24 hours
Walkable	48 hours
Total treat	7 - 8 days
Repainting	8 - 24 hours
Diluent and cleaning of the tools	Fresh water
Presentation	4 lt and 14 lts containers
Conservation	Keep away from extreme temperatures
COV'S	Cat. A/i (legal limit 140 g/l) Max. Cont. 50 g/l

Application

It can be applied by brush or roller to short hair. Walls must be clean, dry and well consolidated, not applied at ambient temperatures and support below 5°C or higher than 35°C and air humidity should be less than 80%. Apply a minimum of two hands crossed to a consumption of approximately 0,750 - 1 Kg/m².

Surface preparation

The surface must be carefully prepared due the durability et correct application of the product. The surface must be clean, dry, free of contaminants, that could adversely affect the adhesion of the membrane. Its maximum of humidity should not exceed 5%. Fresh concrete must be dry for at least 28 days.

Old membranes, dirt, grease, oils, organic substances and dust should be removed mechanically. Also possible irregularities on the surface must be removed. The loose parts of the surface should be repaired.

Suitable for use domestic, not suitable for children.

Cautions

S2	Keep out of the reach of children
S23/24/25	Do not breathe vapors and avoid contact with eyes and skin.
S51	Use only in well-ventilated areas.

According to the Royal Decree 363/1995 (Directive 67/548/EC) and the Royal Decree 255/2003 (Directive 1999/45/EC), not this classified as dangerous product. Data sheet security available to the professional user who requests it.



Distribuidor Oficial de:

Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on it application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

www.delapenia.com

Factory and offices



Trofeo
CC100
Compromiso
a la Calidad

Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)

t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com



Master
Internacional
de Empresas



pinturas de la peña
fábrica de pinturas

WATER POLYURETHANE MEMBRANE

Waterborne Polyurethane Membrane for a waterproofing in transitable places Page 2 de 2



Distribuidor Oficial de:

Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on its application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

www.delapenia.com

Factory and offices



Trofeo
CC100
Compromiso
a la Calidad

Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)

t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com

Master
Internacional
de Empresas

