

PEÑAPIK Dripping Plastic Paint has a beautiful white, and can also be applied with foam roller. Projected to pistol is achieved a very round drop, without wastage, or peeling, as well as a foam roller pore 3, you get a bite of different sizes. It has been conceived for all types of interior surfaces (plasters, cements, etc.), allowing to make all kinds of embossed finishes.

Features



Color	White
Finish	Matt
Specific weight	1,85 gr./cc.
Fixed matter	76 % +/- 1
Performance	1,5 - 2 m ² /Kg depending on the work
Drying time to touch	6-12 hours
Curing time	21 days
Recoat	8-10 hours minimum, maximum without limit
Diluent	Water (maximum 25% in weight)
Presentation	Cans of 5 and 25 Kg.
Conservation	Keep away from extreme temperatures
COV'S	Cat A/a (legal limit 30g/l) content max 25 g/l

Application

On porous surfaces, such as plasters, it is necessary a coat of preparation, that can be the same product PEÑAPIK diluted with water, applying with roller or brush and then it is projected to pistol to obtain the type of "gotelé" that wants. If you want to get a bite, scratch or other type of relief, the product should not be diluted. can be applied by brush, roller airless gun, etc. Before application the surface must be completely clean and dry. Do not apply to temperatures below 5 °C or above 35 °C.

Composition

Water, varied emulsions, best quality loads and other additives chosen for this product.

Suitable for use domestic, not suitable for children.

Cautions

S2	Keep out of the reach of children
S23/24/25	Do not breathe vapours and avoid contact with eyes and skin.
S51	Use only in well-ventilated areas.

According to the Royal Decree 363/1995 (Directive 67/548/EC) and the Royal Decree 255/2003 (Directive 1999/45/EC), not this classified as dangerous product. Data sheet security available to the professional user who requests it.



Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on it application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

www.delapenia.com

Fábrica y oficinas



Trofeo
CC100
Compromiso
a la Calidad

Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)

t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com

