

Synthetic enamel formulated with a careful selection of resins (alkyd-soy and urea), additives and pigments of high quality, to obtain a product with: excellent covering, great hardness, capacity of equalization, filling and leveling Surface.

It is suitable for decorating and protecting all types of surfaces (metals, woods, etc.) both indoors and outdoors, as long as it is intended to achieve a highly decorative and durable finish.

Features

Color	White, black
Finish	Satin smooth
Specific weight	1,14 gr/cc.
Viscosity	110 +/-5 sg copa Ford nº4 a 20º C
Fixed matter	50 +/-5 % in weight (depending on the color)
Drying time	3-9 hours
Recoat	24 hours minimum
Flash point	90°C
COV'S	Max 275 g/l (depending on the color)
Presentation	Cans of 375 ml, 750 ml and 4 lt.



Application

Recommended thickness by hand	30-35 micra
Theorist performance	8 - 12 m ² /l depending on the state of surface
Solvent	Universal, turpentine or turpentine simile
Number of components	1
Method of application	Brush, roller, spray gun
Dilution	5 - 10 %

Surface preparation

Apply on a suitable primer or sealant, depending on whether the surface to be protected is metal or wood. Apply two coats of synthetic enamel to the recommended thickness.

Remarks

When applied to the pistol, the minimum repainting interval is 48-72 hours. When the product is used outdoors the stability of some colors yellow, red and orange live may be inferior to the usual.

Suitable for use domestic, not suitable for children.

Safety

The safety instructions on the packaging label must be followed scrupulously, in addition to complying with the requirements of national or local legislation. As general indications:

Avoid inhalation of solvent vapors and paint mist, as well as contact of liquid paint with skin and eyes.

If applied in confined spaces, forced ventilation should be provided, accompanied by adequate respiratory protection of the skin and eyes, especially when applied to a pistol.

Store in dry and isolated places.

There is a security data sheet available to the professional user who requests it.



Distribuidor Oficial de:

Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on it application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

www.delapenia.com

Fábrica y oficinas



Trofeo
CC100
Compromiso
a la Calidad

Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)

t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com





pinturas de la peña
fábrica de pinturas

PEÑALAC

Satin-Finish Synthetic Enamel

Page 2 of 2



Distribuidor Oficial de:

Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on its application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

www.delapenia.com

Fábrica y oficinas



Trofeo
CC100
Compromiso
a la Calidad

Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)

t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com

Master
Internacional
de Empresas

