



MATT PLASTIC PAINTING M-15

Interior-exterior matt plastic paint

Page 1 of 1

M-15 interior-exterior is a plastic painting based on acrylic copolimeras emulsions, titanium dioxide and other selected raw materials. It has a good power of covering, it is resistant to the exterior. It is characterized by its great dry whiteness and performance, easy to paint by brush and finish.

Features

Color	White
Finish	Matt
Specific weight	1,64 +/-0,05 gr./cc.
Viscosity at time of packaging	110 K.U. a 25 °C
Fixed matter %	68% +/-5
Volume solids %	41% +/-5
Performance	5-a 6 m ² /Kg per coat, depending on the state of surface
Dry film recommended thickness	40-44 micras per coat
Drying time to touch	40 - 60 minutes
Total curing	21 days
Recoat	4 - 6 hours minimum, maximum without limit
Diluent	Clean water
Presentation	Cans of 5 and 23 Kg.
Conservation	Keep away from extreme temperatures
COV'S	Cat A/a (legal limit 30 g/l) content max 25 g/l



Application

It can be applied on any construction material, plaster, cement, plaster, etc. Its application can be brushed, roller or sprayed. Before application the facing must be completely clean, taking into account that it should not be applied at temperatures below 5 °C or above 35 °C.

Composition

Water, emulsions, titanium dioxide, calcium carbonates and other loads chosen for this product.

Suitable for domestic use. Keep out of reach of children

Cautions

- S2 Keep out of reach of children.
 S23/24/25 Do not breathe its vapors and avoid contact with eyes and skin.
 S51 Use in well ventilated places.

According to Royal Decree 363/1995 (Directive 67/548/EEC) and Royal Decree 255/2003 (Directive 1999/45/EC), this is not classified as a dangerous product. Safety data sheet available for professional user on request.



Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on its application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

www.delapenia.com

Fábrica y oficinas



Ctra. Orgaz, s/n
 Apdo. 25
 45400 Mora (Toledo)

t: +34 925 300 409
 f: +34 925 341 082
 e: info@delapenia.com

