

Interior plaster suitable for recapping usual plaster and/or cement supports.

Features



Useful Life (S / ITE C1 / 51-L)	1,5 - 2 Hours
Fire behavior	A1- No fuel
Granulometry	300 microns - Medium
pH (S/ITE CI/18-L)	6,5 - 7,5
Shore hardness C (S / ITE CI / 22-L)	81
Conservation	12 Months
Cleaning Tools	Con water
Performance Kg powder / m2 in 1 mm thickness	1,16 - 1,19
Yield Kg paste / m2 in 1 mm thickness	1,64 - 1,73
Adherence (S / Annex 2 NF P 74202-1 DTU 59.2)	
On plastic paint	Higher than 0,8 MPa
On cement	Higher than 0,8 Mpa
Density (S / ITE CI / 53-L) Powder	0,92 Gr/Lt
Density (S / ITE CI / 53-L) Paste	1,70 Gr/Lt
Deep drying times (S / ITE CI / 52L)	
Concrete (Thickness medium layer 2 mm)	More than 8 hours
Painting (Thickness medium layer 2 mm)	More than 8 hours
Plaster (Thickness medium layer 2 mm)	5-6 hours
Presentation	Sacks of 15 Kg
Conservation	Keep away from extreme temperatures

How to use

Knead with water at a rate of 43-45%. For each bag of 15 Kg, 6.45 to 6.75 liters of water should be used for mixing. The kneading must be done manually or mechanically using an electric mixer. Let the pasta rest for a few minutes and then apply.

For the capping of cavities, it is recommended to use a spatula of medium size, which allows to press well into the hollow. In cases where possible, ensure that the width of the spatula is slightly greater than the size of the cavity. The smoothing operation is always done vertically from bottom to top with a wide blade, putting material and removing the excess then trying to smooth and cover all the defects of the surfaces. The connections are made on the contrary, from top to bottom.

When the material dries, proceed to sanding and then give another coat of plaster horizontally from right to left, taking the joints from left to right.

Finally, after the drying of this second coat, the surface is sanded and, if no imperfection is observed, the left is painted, taking the joints from left to right.

Properties and use

Easy to apply, smooth and sand.

Smooth and fine finishes.

It does not start when passing iron

Good hiding power

Indicated for the renovation and leveling of interior supports

Smoothing of walls with defects (scratches, scratches, blows, etc.)

MAXIMUM THICKNESS PER 8 MM LAYER



Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on its application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

www.delapenia.com

Factory and offices



Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)

t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com



Application on site

The support must be healthy, clean, consistent, free of moisture and free of all traces of saltpeter, fungi, microorganisms, dust, grease or any type of material that may hinder the good adherence of the product to the support.

Information of interest

The manufacturing process is controlled by batches, which allows traceability against any incident. The quality system used includes the design of each item and the controls in the elaboration of the same, both of the raw materials used, ensuring the uniformity of the manufacture, and the final product obtained. The use of eco technologies in the manufacturing processes of our facilities, allow the realization of a work efficiently, without prejudice to the environment that surrounds us.

Non-flammable product.

Avoid that the product comes in contact with the skin and eyes.

In the area of application, smoking, eating and drinking should be prohibited.

Comply with the legislation on safety and hygiene at work.

Keep the product in a dry place, in original containers properly closed.

Store the containers between 5° C and 35° C.

First Aid-personal. Protective measures

Inhalation: Although it does not present any specific risk, it is recommended, for prolonged use, the use of filter masks.

Eye contact: In case of wearing contact lenses, remove them. Wash your eyes thoroughly with clean, fresh water for at least 10 minutes, pulling the eyelids up and seek medical attention. Wear protective glasses.

Skin contact: Wash with soap and water or a suitable skin cleanser. Protective creams can help protect exposed skin areas.

Ingestion: If accidentally swallowed, seek medical attention immediately and remain at rest. Never cause vomiting.

Observations

For an adequate use and correct application of the product, it is essential to read its technical sheet beforehand. The data provided in this data sheet have been obtained under normal laboratory conditions and on standardized supports, which may vary depending on the conditions of application (absorption of the substrate, applied thickness, mixing water, temperature and humidity)).

The working conditions of the users are beyond our control.

The product must not be used for purposes other than those specified. It is recommended to strictly follow the employment recommendations

It is essential the prior recognition to each application, the state of the funds.

We advise you to read carefully the **preparation of sleep section**.

Use the product within its useful life.

After this time, unfavorable properties can be obtained.



Distribuidor Oficial de:

Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on its application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

www.delapenia.com

Factory and offices



Trofeo
CC100
Compromiso
a la Calidad

Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)

t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com



Master
Internacional
de Empresas



PEÑAPLAST POWDER RENOVATION

Filler Indoor Powder (thick coat)

Page 3 de 4

The established times for both the useful life of the product and its setting, are calculated under normal laboratory conditions, therefore they are indicative, and may vary depending on environmental conditions.

Do not mix with any material, as it will not preserve its technical characteristics.

Do not apply on non-absorbent backgrounds.

Admits finished with traditional water paint. When in doubt, we recommend carrying out a test on the plaster, prior to painting.

The permanent state of heat is not suitable in the plasters of the range, since its mineral components do not contain clays or flame retardants. Therefore, it is totally discouraged to apply on reheated funds.

It is not advisable to wet the supports. The products of the range have the property of retaining the water of kneading, allowing a good workability without starting.

The components of the rock are generally hygroscopic and absorb the moisture contained in the air.

It is essential to always apply in favorable conditions of relative humidity.

It is not advisable to apply the product on old paints that can be removed with the application of the plaster.

We have at your disposal a technical-commercial team that will advise you on any questions or queries



Distribuidor Oficial de:

Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on its application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

www.delapenia.com

Factory and offices



Trofeo
CC100
Compromiso
a la Calidad

*Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)*

*t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com*



Master
Internacional
de Empresas



pinturas de la peña
fábrica de pinturas

PEÑAPLAST POWDER RENOVATION

Filler Indoor Powder (thick coat)

Page 4 de 4



Distribuidor Oficial de:

Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on its application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

www.delapenia.com

Factory and offices



Trofeo
CC100
Compromiso
a la Calidad

*Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)*

*t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com*

Master
Internacional
de Empresas

