

De la Peña

pinturas de la peña
fábrica de pinturas**ACRYLIC PAINT V/64**

Acrylic Paint for Interior-Exterior

Page 1 de 2

Our paint V/64 is an acrylic paint formulated with acrylic copolymers, titanium dioxide, extenders, selected fillers and chosen additives. It is designed to obtain a product with good opacity, good resistance to weather due to its hardness and waterproof qualities. It provides high whiteness and performance.

Features

Color	White
Finish	Matt
Specific weight	1,73 gr./cc. +/- 0.05
Viscosity at time of packaging	115K.U. +/- 5 a 25° C
Fixed matter %	71% +/- 2
Volume solids %	42 % +/- 2
Performance	5 - 6 m ² /kg per coat depending on the state of the surface
Wet film recommended thickness	100-110 micras per coat
Dry film recommended thickness	40-45 micras per coat
Dry-to-touch time	40 - 60 minutes
Curing time	21 days
Recoat	6 - 8 hours minimum. Maximum without limit
Thin with	Clean water
Presentation	1, 5, 10 and 23 kg cans
Conservation	Keep away from extreme temperatures
VOC's	Cat A/a (legal limit 30 g/l). Maximum content 25 g/l

**Application**

It can be applied on any building material, plaster, cement, etc. It can be applied by brush, roller or spray. Before application, the surface must be completely clean and dry.

First coat should be thinned with 15-20% of clean water, and the second with 8-10%.

Do not apply when air and surface temperatures are below 5° C or above 35° C and always 2-3°C above the dew temperature.

Composition

Water, emulsions, titanium dioxide, carbonates of calcium and other fillers selected for this product.

Suitable for domestic use. Keep out of reach of children.

Cautions

- P101 If medical advice is needed, have product container or label at hand.
 P102 Keep out of reach of children.
 P103 Read label before use.
 P501 Dispose of contents and / or their container according to the separated collection system used in your municipality.



Distribuidor Oficial de:

Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on its application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

www.delapenia.com

Factory and offices



Trofeo
CC100
Compromiso
a la Calidad

Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)

t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com



Master
Internacional
de Empresas



pinturas de la peña
fábrica de pinturas

ACRYLIC PAINT V/64

Acrylic Paint for Interior-Exterior

Page 2 de 2

EUH208 Contains 2-octyl-2H-isothiazon-3-one. Mixture of: 5-chloro-2-methyl-2H-isothiazolin-3-one [EC no. 247-500-7]; 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1). May produce an allergic reaction.

According to Royal Decree 363/1995 (Directive 67/548/EEC) and Royal Decree 255/2003 (Directive 1999/45/EC), this is not classified as a dangerous product. Safety data sheet available for professional user on request.



Distribuidor Oficial de:

Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on its application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

www.delapenia.com

Factory and offices



Trofeo
CC100
Compromiso
a la Calidad

Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)

t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com

Master
Internacional
de Empresas

